

Alkenz Fabrics

Style SUNSHADOW 3000 CA Series □ Openness Factor 3%

• Composition	35% Polyester, 65% PVC	• Tensile Strength	Warp 150 / Weft 120 daN/5cm
• Openness Factor	Average 3%	• Tearing Strength	Warp 4.5 / Weft 6.9 daN
• Weight	9.44oz/yd ² (320 g/m ²) +5%	• Color Fastness	Grade 8
• Thickness	0.018" (0.45mm) + 5%	• Fabric Count	47 ends x 30 picks/ sq inch
• Standard Width	98.2"	• Fire Classification	M1, B1, B2
• Standard Length	33 yd / roll		NFPA 701-99, CA US Title 19

Fenestration Properties – Alkenz 3000 CA Series (approximate)

Description	Ts	Rs	As	Tv	S/C (International)		
					1/8" CL	1/4" CL	1/4" HA
CA01 White/White	19	66	15	13	0.34	0.34	0.32
CA02 White/Moccasin	12	54	34	7	0.41	0.40	0.35
CA03 White/Light Gray	15	58	27	9	0.42	0.38	0.34
CA04 White/Dim Gray	13	50	37	9	0.44	0.43	0.37
CA08 Charcoal/Bronze	13	55	32	8	0.39	0.38	0.34
CA09 Charcoal/Charcoal	12	52	36	9	0.42	0.41	0.40
CA10 Charcoal/Dim gray	14	50	36	8	0.44	0.43	0.37
CA12 White/Brown	12	44	44	8	0.48	0.47	0.39
CA30 Gray/Light Gray	5	26	69	4	0.59	0.56	0.44

Environment Friendly



Flammability



M1
B1
B2
NFPA 701

Anti Bacteria



ASTM G21
ASTM G22

The solar optical properties are used to calculate the shading coefficient. The shading coefficient represents the percentage of solar heat gain that is transmitted to the interior through the glass and shading system. Darker colors provide maximum glare reduction and visibility.

Style SUNSHADOW 3000 CA Series

Specification Data Sheet

CACO, Inc., Window Fashions

119 Perma R Road • Johnson City, TN 37604

(800) 552-5278 • Fax (866) 926-5836

Web: www.cacoinc.com • Email: customerservice@cacoinc.com