

Style SUNSHADOW 4700 P Series □ Openness Factor <.1%

•Composition	20% Polyester, 80% PVC	•Tensile Strength	Warp 265 / Weft 100 daN/5cm
•Openness Factor	Less than 1%	•Tearing Strength	Warp 8.1 / Weft 4.6 daN
•Weight	18.58 oz/yd ² 630 g/m ² +5%	•Color Fastness	Grade 8
•Thickness	0.035"	•Fabric Count	50 ends x 16 picks/ sq inch
•Standard Width	98.4"	•Fire Classification	M1, B1, B2
•Standard Length	33yd/roll		NFPA 701-99, CA US Title 19

Fenestration Properties – Alkenz 4700 P Series (approximate)

Description	Ts	Rs	As	Tv	S/C (International)		
					1/8" CL	1/4" CL	1/4" HA
P001 White/White	13	74	13	7	0.27	0.27	0.29
P012 White/Beige/Beige	9	65	26	5	0.32	0.32	0.31
P013 White/Gray/Gray/Gray	7	57	36	3	0.37	0.37	0.34
P015 White/Blue Gray/White	8	60	32	3	0.35	0.34	0.32
P016 White/Light Gray/Light Pink	5	52	43	2	0.39	0.38	0.32
P017 White/Light Gray/Blue Gray	5	49	46	2	0.41	0.40	0.37

Environment Friendly



Flammability



M1
B1
B2
NFPA 701

Anti Bacteria



ASTM G21
ASTM G22

The solar optical properties are used to calculate the shading coefficient. The shading coefficient represents the percentage of solar heat gain that is transmitted to the interior through the glass and shading system. Darker colors provide maximum glare reduction and visibility.

Style SUNSHADOW 4700 P Series

Specification Data Sheet

CACO, Inc., Window Fashions

119 Perma R Road • Johnson City, TN 37604

(800) 552-5278 • Fax (866) 926-5836

Web: www.cacoinc.com • Email: customerservice@cacoinc.com