

Alkenz Fabrics

Style SUNSHADOW 4000 L Series □ Openness Factor 5%

•Composition	27% Polyester, 73% PVC	•Tensile Strength	Warp 205 / Weft 160 daN/5cm
•Openness Factor	Average 5%	•Tearing Strength	Warp 11.8 / Weft 10.0 daN
•Weight	13.12 oz/yd ² 445 g/m ² +5%	•Color Fastness	Grade 8
•Thickness	0.025" (0.65mm) +5%	•Fabric Count	36 ends x 25 picks/ sq inch
•Standard Width	98.4"	•Fire Classification	M1, B1, B2
•Standard Length	33 yd/roll		NFPA 701-99, CA US Title 19

Fenestration Properties – Alkenz 4000 L Series (approximate)

Description	Ts	Rs	As	Tv	S/C (International)		
					1/8" CL	1/4" CL	1/4" HA
L101 White/White/Beige	15	66	19	10	0.32	0.33	0.32
L102 White/White/Sable	17	62	21	12	0.36	0.36	0.33
L103 White/White/Tree Brown	21	55	24	15	0.39	0.38	0.35

Environment Friendly



Flammability



M1
B1
B2
NFPA 701

Anti Bacteria



ASTM G21
ASTM G22

The solar optical properties are used to calculate the shading coefficient. The shading coefficient represents the percentage of solar heat gain that is transmitted to the interior through the glass and shading system. Darker colors provide maximum glare reduction and visibility.

Style SUNSHADOW 4000 L Series
Specification Data Sheet

CACO, Inc., Window Fashions

119 Perma R Road • Johnson City, TN 37604

(800) 552-5278 • Fax (866) 926-5836

Web: www.cacoinc.com • Email: customerservice@cacoinc.com