

Alkenz Fabrics

Style SUNSHADOW VIEW R Series □ Openness Factor 15%

•Composition	27% Polyester, 73% PVC	•Tensile Strength	Warp 180 / Weft 188 daN/5cm
•Openness Factor	Average 15%	•Tearing Strength	Warp 14.1 / Weft 14.0 daN
•Weight	455 gram/ sqm +5%	•Color Fastness	Grade 8
•Thickness	0.32" (0.83mm) +5%	•Fabric Count	46 ends x 48 picks/ sq inch
•Standard Width	98.4"	•Fire Classification	M1, B1, B2
•Standard Length	33 yd/roll		NFPA 701-99, CA US Title 19

Fenestration Properties – Alkenz VIEW R Series (approximate)

Description	Ts	Rs	As	Tv	S/C (International)		
					1/8" CL	1/4" CL	1/4" HA
R100 White/White	33	56	11	29	0.45	0.44	0.38
R102 White/Sable	27	49	24	23	0.48	0.47	0.39
R103 White/Gray	26	43	31	25	0.52	0.51	0.41
R105 White/Blue Gray	26	44	30	24	0.52	0.50	0.41
R401 Dim Gray/Dim Gray	20	26	54	20	0.63	0.60	0.46
R402 Dim Gray/Light Gray	19	20	61	19	0.66	0.63	0.48
R900 Charcoal/Charcoal	15	4	81	17	0.76	0.72	0.52

Environment Friendly



Flammability



M1
B1
B2
NFPA 701

Anti Bacteria



ASTM G21
ASTM G22

The solar optical properties are used to calculate the shading coefficient. The shading coefficient represents the percentage of solar heat gain that is transmitted to the interior through the glass and shading system. Darker colors provide maximum glare reduction and visibility.

Style SUNSHADOW VIEW R Series

Specification Data Sheet

CACO, Inc., Window Fashions

119 Perma R Road • Johnson City, TN 37604

(800) 552-5278 • Fax (866) 926-5836

Web: www.cacoinc.com • Email: customerservice@cacoinc.com