

Alkenz Fabrics

Style SUNSHADOW 3000 Net Series □ Openness Factor 3%

•Composition	25% Polyester, 75% PVC	•Tensile Strength	Warp 197 / Weft 167 daN/5cm
•Openness Factor	Average 3%	•Tearing Strength	Warp 7.4 / Weft 7.0 daN
•Weight	13.12 oz/yd ² (445 g/m ²) +5%	•Color Fastness	Grade 8
•Thickness	0.022" (0.57mm) +5%	•Fabric Count	54 ends x 46 picks/ sq inch
•Standard Width	98.4"	•Fire Classification	M1, B1, B2 NFPA 701-99, CA US Title 19
•Standard Length	33 yd/roll	•Anti Bacteria	ASTM G21, ASTM G22

Fenestration Properties – Alkenz 3000 Net Series 3% (approximate)

Description	Ts	Rs	As	Tv	S/C (International)		
					1/8" CL	1/4" CL	1/4" HA
N001 White/White	17	65	18	10	0.32	0.31	0.31
N002 White/Beige	16	55	29	9	0.40	0.39	0.34
N003 White/Gray	10	43	47	6	0.46	0.45	0.37
N201 Beige/Beige	12	52	36	8	0.42	0.41	0.35
N301 Gray/Gray	7	31	62	4	0.54	0.52	0.43
N801 Bronze/Bronze	2	8	90	2	0.68	0.65	0.47
N901 Charcoal/Charcoal	2	4	94	3	0.71	0.67	0.49
N902 Charcoal/Bronze	2	5	93	3	0.70	0.65	0.50
N903 Charcoal/Gray	3	15	82	2	0.64	0.61	0.45

Environment Friendly



Flammability



M1
B1
B2
NFPA 701

Anti Bacteria



ASTM G21
ASTM G22

The solar optical properties are used to calculate the shading coefficient. The shading coefficient represents the percentage of solar heat gain that is transmitted to the interior through the glass and shading system. Darker colors provide maximum glare reduction and visibility.

Style SUNSHADOW 3000 Net Series 3%

Specification Data Sheet

CACO, Inc., Window Fashions

119 Perma R Road • Johnson City, TN 37604

(800) 552-5278 • Fax (866) 926-5836

Email: customerservice@cacoinc.com • Web: www.cacoinc.com