

Alkenz Fabrics

Style SUNSHADOW 3000 Net Series □ Openness Factor 10%

• Composition	25% Polyester, 75% PVC	• Tensile Strength	Warp 167 / Weft 154 daN/5cm
• Openness Factor	Average 10%	• Tearing Strength	Warp 6.8 / Weft 6.2 daN
• Weight	11.36oz/yd ² (385 g/m ² +5%)	• Color Fastness	Grade 8
• Thickness	0.020" (0.52mm) +5%	• Fabric Count	48 ends x 38 picks/ sq. inch
• Standard Width	98.4"	• Fire Classification	M1, B1, B2 NFPA 701-99, CA US Title 19
• Standard Length	33 yd/roll	• Anti Bacteria	ASTM G21, ASTM G22

Fenestration Properties – Alkenz 3000 Net Series 10% (approximate)

Description	Ts	Rs	As	Tv	S/C (International)		
					1/8" CL	1/4" CL	1/4" HA
N001 White/White	28	57	15	20	0.39	0.38	0.35
N002 White/Beige	24	54	22	20	0.45	0.44	0.39
N091 Cream/Cream	29	61	10	25	0.41	0.38	0.37
N203 Beige/Gray	17	38	45	15	0.55	0.52	0.43
N801 Bronze/bronze	11	5	84	12	0.73	0.70	0.52
N901 Charcoal/Charcoal	11	3	86	13	0.76	0.72	0.54
N903 Charcoal/Gray	12	15	73	13	0.70	0.66	0.50

Environment Friendly



Flammability



M1
B1
B2
NFPA 701

Anti Bacteria



ASTM G21
ASTM G22

The solar optical properties are used to calculate the shading coefficient. The shading coefficient represents the percentage of solar heat gain that is transmitted to the interior through the glass and shading system. Darker colors provide maximum glare reduction and visibility.

Style SUNSHADOW 3000 Net Series 10%
Specification Data Sheet

CACO, Inc., Window Fashions

119 Perma R Road • Johnson City, TN 37604

(800) 552-5278 • Fax (866) 926-5836

Email: customerservice@cacoinc.com • Web: www.cacoinc.com