

Alkenz Fabrics

Style SUNSHADOW 4000 Net Series □ Openness Factor 10%

- | | | | |
|--------------------------|------------------------|------------------------------|---|
| • Composition | 27% Polyester, 73% PVC | • Tensile Strength | Warp 255 / Weft 110 daN/5cm |
| • Openness Factor | Average 10% | • Tearing Strength | Warp 27.1 / Weft 24.1 daN |
| • Weight | 470 g/sqm + 5% | • Color Fastness | Grade 8 |
| • Thickness | 0.025" (0.66mm) + 5% | • Fabric Count | 36 ends x 29 picks/ sq inch |
| • Standard Width | 98.4" | • Fire Classification | M1, B1, B2
NFPA 701-99, CA US Title 19 |
| • Standard Length | 33 yd/roll | • Anti Bacteria | ASTM G21, ASTM G22 |

Fenestration Properties – Alkenz 4000 Net Series 10% (approximate)

Description	Ts	Rs	As	Tv	S/C (International)		
					1/8" CL	1/4" CL	1/4" HA
N001 White/White	24	61	15	15	0.33	0.35	0.33
N002 White/Beige	21	53	26	13	0.41	0.40	0.37
N003 White/Gray	18	39	43	12	0.49	0.48	0.40
N201 Beige/Beige	22	45	33	14	0.46	0.45	0.38
N301 Gray/Gray	16	25	59	10	0.58	0.57	0.45
N901 Charcoal/Charcoal	14	2	84	9	0.75	0.71	0.53
N902 Charcoal/Bronze	13	4	83	9	0.74	0.70	0.52

Environment Friendly



Flammability



M1
B1
B2
NFPA 701

Anti Bacteria



ASTM G21
ASTM G22

The solar optical properties are used to calculate the shading coefficient. The shading coefficient represents the percentage of solar heat gain that is transmitted to the interior through the glass and shading system. Darker colors provide maximum glare reduction and visibility.

Style SUNSHADOW 4000 Net Series 10%

Specification Data Sheet

CACO, Inc., Window Fashions

119 Perma R Road • Johnson City, TN 37604

(800) 552-5278 • Fax (866) 926-5836

Email: customerservice@cacoinc.com • Web: www.cacoinc.com